
# ABOUT CABLE TIES



## What is a cable tie?

A cable tie is a band or length of strap, manufactured from a class of polymeric materials known as polyamides (Nylon 6/6). The width, length and head area employ ratcheting mechanisms, which allow for locking as necessary for bundling items together.



# Materials: Polyamide Nylon 6/6 Family

Natural
Heat Stabilized
UV Resistant
High Impact
Metal Detectable
Air Handling
Cold Weather
Colors (17)
Propylene

#### **Material Certification:**

Polyamide: Nylon 6/6
Flammability Rating – 94V2
Relative Viscosity (RV) (45-51)
Tensile Strength – 78 min (MPa)
Moisture – (.08-.20)
Meets ASTM D4066 PAOIII and
FMVSS 302 requirements

Nominal Strain @ break; (elongation) – 17.5 (min) (%)

#### **ACT Cable Tie Certifications:**

ISO 9001:2015 Registered

UL Listed ANSI/UL62275 Cable Ties & Fixing Devices

Mil Spec Certified AS23190; QPL Qualified (3 yr cycle); Meet requirements of SAE-AS3367-1 Specifications

Reach – SVHC Declaration – European Chemical Agency

RoHS2 – European Union's Restriction of Use of Hazardous Substance in Electrical and Electronic Equipment

**Conflict Mineral Statement** 

Food Contact Application Natural (-9)

CA. Prop 65 (California Proposition 65)

CSA Standard (Canadian Standards Association) : C22.2 No 0

C22.2 No. 18.5/UL1565

### Strengths & Sizes (Series):

Mounting Hole 5"-30lb, (50lb)7", 11", 14", 14"-120lb

**18 lb Series – Miniature** 4", 6", & 8"

**40 lb Series – Intermediate** 5", 8", 11", 14" & 6"PMW


**50 lb Series - Standard** 7", 11", 14", 17", & 21"

**120 lb Series – Heavy Duty** 8", 14", 18", 24", 30" & 36"

**175 lb Series – Extra Heavy Duty** 24", 36", & 48"

**250 lb Series – Extra Heavy Duty** 22"

# ABOUT CABLE TIES



# **Nylon Drying Specification:**

Nylon – Hygroscopic Moisture Level - .08 – 2.0% Dry Material – Critical Control Moisture to - .001% Residence Drying Time @ 165°F for 4 hrs

## **Packaging Specification:**

Compliant to UL and Mil Spec standards to the smallest unit pack size.

\*Shelf life is determined by the nature of the warehouse:

Controlled warehouse (+ or - 5°F)

= 6 mos. – 1 yr.

Uncontrolled = 3-4 mos.

\*Product remains in sealed bags. Ideal storage in original sealed package, in 50% RH, at 70°F/21°C, out of direct sunlight, until installation.

# **Machine Processing:**

Molding Machines are built to ACT specs which include: Material residence time Heat profile (barrel) Injection speeds Recovery speeds

# **ACT Advantages**:

- Made in USA
- State of the Art Facility and Equipment
- UL, UR, CSA, Mil-Spec, and RoHS Compliant Products
- Ergonomic Design
- Highest Tensile Strength in the Industry
- Lowest Insertion Force
- Optimum Flexibility
- Single Method of Failure
- Consistent Vibrant Colors
- Custom Labeling





